




B&E INTERNATIONAL LTD.

PRINTOFIX LACCA PEARL

INNOVATION | QUALITY | KNOW-HOW

www.b-and-e.com

GIRLS
WILL
RUN THE
WORLD



PRINTOFIX CLEAR PEARL

PRINTOFIX CLEAR PEARL is a ready-made, specially formulated printing paste, which gives an attractive pearl shiny appearance to the fabric.

Chemical properties:

Chemical description: Binders and synthetic thickeners.

Appearance: Slightly beige medium viscosity paste.

pH value: CA. 8.5+ 0.3

Specific Gravity: CA. 1.1

Fields of application:

This product is suitable for use in a wide variety of printing methods, such as table, flat bed, rotary screen and roller application.

Recommended use:

Shading:

PRINTOFIX CLEAR PEARL is ready easy to use paste.

0.5% of pigment according to desired shade

99.5% PRINTOFIX CLEAR PEARL

A coarse screen is recommended to avoid clogging, for instance 60 mesh or 48T.

The viscosity of PRINTOFIX CLEAR PEARL can be reduced by adding up to 5% of water and increased by adding 2 g/kg THICKENER BGF-500 while stirring. When more than one color is printed, PRINTOFIX CLEAR PEARL should be applied last in order to avoid build-up effect on a following screen.

Screen should be washed immediately after printing to avoid drying in.

After printing, the fabric must be dried and cured under normal conditions, 3-4 minutes at 160°C.

Prints cured under the above conditions have excellent all-around fastnesses.

The cured prints can be calendared.

Fastness properties on cotton:

| | |
|----------------|------------|
| Xenon light: | 7 |
| Crock dry/wet: | 4-5/4 |
| Dry cleaning: | 4 |
| Washing: | 95°C F 4-5 |
| | CO 5 |
| | CV 5 |
| | 150 °C F 5 |
| | CO 5 |
| | PE 5 |

Fastness properties on cotton:

Thermo fixing: 180°C F 5
 CO 5
 PE 5

 210°C F 5
 CO 5
 PE 4-5

Peroxide Bleaching F 4-5
 CO 5
 CV 5

*** The information in this bulletin is given as a service only, and is not to be taken as a guarantee.*


Storage:

Should be protected against frost and stored at a temperature between 5-35°C. The package should be kept tightly closed after use to avoid drying out.

Packing:


Plastic drums 60-120 kg.

Printing results



Lawless

GIRLS
WILL
RUN THE
WORLD



THANK YOU!

6 Hamasor Str.
58815 Holon, Israel

+972 3 559 0213
+972 559 6636

support@b-and-e.com
www.b-and-e.com

